

BLURAM HS

Product Information Sheet

Monolithic Refractory

Bluram HS is a versatile, mullite based phosphate bonded mouldable. Finds many uses in various applications.

Maximum Service Temp: 1700°C
Maximum Grain Size: 7 mm
Standard Packaging*: Carton - 25kg
Estimated Coverage** 2420 kg/m³
Initial Heat Up Schedule: D
Water Addition: N/A

Reversible Thermal Expansion @ 1000°C: 0.7%
Curing Time: N/A
Storage Life: Up to 6 Months
Setting: Chemical / Heat
Abrasion Loss: 4-7cc
ASTM C704

Chemical Analysis

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	TiO ₂	CaO	Alkalies	P2O5	Other
72	20	0.8	1.8	0.2	0.4	4.3	0.5

Typical Physical Properties: on rammed samples

Prefired To	Bulk Density	Cold Crushing Strength	Cold Modulus of Rupture	Permanent Linear Change
°C	kg/m ³	MPa	MPa	%
110	2470	16.00	5.00	-0.70
815	2420	26.00	7.50	-0.70
1400	2410	40.00	13.00	-0.40
1500	2400	37.00	-	+0.70

Other Physical Properties

Prefired To	Apparent Porosity	Thermal Conductivity	Hot Modulus of Rupture	Permanent Volume Change
°C	%	W/mK	MPa	%
110	-	-	-	-
815	-	1.33	-	-
1400	-	1.31	-	-
1500	-	-	-	-

Formerly:

Product Number: LES10072

MSDS Reference: Bluram HS msds

Effective Date: Oct 12

Revision: 0

*Please enquire for other packaging options

**Estimated coverage on gungrades does not include rebound

The physical and/or chemical properties and specifications of the product set forth above represent typical average results obtained in accordance with generally accepted Australian standard test methods conducted under controlled conditions, and are subject to normal manufacturing variations. Vesuvius reserves the right to modify the properties and specifications at any time without prior notice.

NO WARRANTY IS EXPRESSED OR IMPLIED REGARDING THE ACCURACY OF THIS INFORMATION, THE SUITABILITY OF THE PRODUCT FOR A PARTICULAR PURPOSE, OR THE RESULTS TO BE OBTAINED BY THE USE OF THE PRODUCT. USERS EXPRESSLY ASSUME ALL RISKS AND LIABILITIES ARISING FROM THE USE OF OR RELIANCE UPON THIS INFORMATION.

Form No.: VA-F-053

UNCONTROLLED COPY

