



CGT 1200 TS LEN71546 MX7 CASB

Monolithic Refractory
Product Information

Revision: B.00

Date: 02 Feb 2018

A versatile light weight refractory suitable for cast, gunned or trowelled use. Designed for insulating backup linings. Refer to separate sheet for additional typical properties.

Service Temperature:	1200 °C	Material Required:	950 kg/m ³
Typical Water Required:	50 - 54 %	Maximum Grain Size:	5 mm
Trowelling Consistency:	55 - 60 %	Shelf Life:	12 months

Chemical Analysis

SiO ₂	TiO ₂	Al ₂ O ₃	Fe ₂ O ₃	CaO	MgO	Alkali
30.0	2.0	42.0	3.0	17.0	4.5	1.6

Typical Physical Properties

Tested in accordance with Australian Standards

Prefired to (°C)	Bulk Density (kg/m ³)	Cold Crushing Strength (N/mm ²)	Cold Modulus of Rupture (N/mm ²)	Permanent Linear Change (%)
110	1050	2.5	1.0	-0.2
1000	950	1.0	0.5	-1.3

Other Physical Properties

Tested in accordance with Australian Standards

Prefired to (°C)	Apparent Porosity (%)	Thermal Conductivity (W/m.K)	Hot Modulus of Rupture (N/mm ²)	Permanent Volume Change (%)
1000	-	0.27	-	-

Physical Properties on CAST Samples

Formerly:

Drying & Firing:	LEA.7802	Installation Method:	N/A	Mixing / Installation:	LEN.7302
Shotcreting:	N/A	Pumping:	N/A	MSDS Reference:	CGT 1200 SDS

The physical and/or chemical properties and specifications of the product set forth above represent typical average results obtained in accordance with generally accepted standard test methods conducted under controlled conditions, and are subject to normal manufacturing variations. Vesuvius reserves the right to modify the properties and specifications at any time without prior notice.

NO WARRANTY IS EXPRESSED OR IMPLIED REGARDING THE ACCURACY OF THIS INFORMATION, THE SUITABILITY OF THE PRODUCT FOR A PARTICULAR PURPOSE, OR THE RESULTS TO BE OBTAINED BY THE USE OF THE PRODUCT. USERS EXPRESSLY ASSUME ALL RISKS AND LIABILITIES ARISING FROM THE USE OF OR RELIANCE UPON THIS INFORMATION.